

No. AJD201203114

Date: JUN.27, 2012

Page 1 of 5

The following sample(s) was / were submitted and identified on behalf of the client as:

Sample Description: PolyFLAT Display System

Type/Style:

Test Requested:

To determine the flammability (building materials class B1) in accordance with DIN 4102-1 (May 1998) Fire behaviour of building materials and elements Part 1: Classification of building materials, Requirements and testing

Test Results: -- See attached sheet --

Conclusion:

The tested sample **meets** the low flammability requirements of class B1 of building materials under DIN 4102-1 (May 1998).

There is no fall-off of burning material.

Test Period:

Sample Receiving Date

: JUN.12, 2012

Test Performing Date

: JUN.12, 2012 TO JUN.26, 2012

Signed for and on behalf of SGS-CSTC Co., Ltd.

Allen Zou

Technical Supervisor

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.
htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_a-document.htm. Attention is drawn to the limitation of its instruction is usues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its instruction only and within the limits of Client's Instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from secretary at the first and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any thousunders are its original and offenders may be prosecuted to the full extent of the law. Unlikes otherwise market the first of the law.

Unlikes otherwise market the first of the content of the content or appearance of this document is unlikeful and offenders may be prosecuted to the full extent of the law.

Unlikes otherwise market the first of the content of the law.



No. AJD201203114

Date: JUN.27, 2012

Page 2 of 5

I. Test conducted

This test was conducted as per DIN 4102-15:1990, DIN 4102-16:1998 and DIN 4102-1:1998 Clause 6.2. Classification in according to DIN 4102-1 (May 1998) Clause 6.1-Class B1 materials

II. Sample details

General description	PolyFLAT Display System
Color / Density	Grey / About 451g/m ²
Size of sample	1000 mm×190 mm & 190 mm×90 mm

Conditioning

Prior to testing, the sample was conditioned at least 14 days to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 6 %.

III. Test results

1) "Brandschacht" Test according to DIN 4102-15 &16

Exposed surface: The Front face

	Results of "Brandscha	acht" Tes	t (part 1)				
Line		Unit	Test assemblies No.				
No.		Onit	Α	В	С	D	
1	Specimen fixings according to DIN 4102 part 15, table	-	1				
2	Max. flame height above lower sample edge;	cm	30				
3	Time 1)	min:s	0:01				
	Melting/burning through						
4	Time 1)	min:s	0:06				
	Back of specimen						
5	Flaming/glowing, Time 1)	min:s	0:06				
6	Discolouring, Time 1)	min:s	0:04				
	Burning droplets		NO				
7	Begin 1)	min:s	/				
	Amount		/				
8	Specimen material falling off in separate droplets		/				
9	Specimen material falling off continuously		./				

To be continued...



No. AJD201203114

Date: JUN.27, 2012

Page 3 of 5

	Results of "Brandscha	acht" Tes	t (part 2)					
Line				Test assemblies No.				
No.		Offic	Α	В	С	D		
	Burning parts		NO					
10	Begin 1)	min:s	/					
11	Parts of sample falling off separately		/					
12	Parts of sample falling off continuously		/					
13	Duration of continued combustion on mesh base (max.)	min:s	NO					
	Burner flame impairment by dripping/falling material		NO					
14	Time 1)	min:s	/					
	Premature ending of test		/					
15	End of burning at specimen 1)	min:s	/					
16	Time when test terminated (if applicable) 1)	min:s	/					
	Burning after end of test		NO					
17	Duration	min:s	/					
18	Number of specimens		/					
19	Front of specimen		/					
20	Back of specimen		/					
21	Height of flame	cm	/					
	Glowing after end of test		NO					
22	Duration	min:s	/					
23	Number of specimens		/					
24	Front of specimen		/					
25	Back of specimen		/					
26	Top half of specimen		/					
27	Bottom half of specimen	I	1					

To be continued...



No. AJD201203114

Date: JUN.27, 2012

Page 4 of 5

	Results of "Bra	ndschacht" Tes	t (par	t 3)				
Line		Unit	Test assemblies No.					
No.		Offic	Α		В	С	D	
	Residual length							
28	Single results	0.00	80	75				
26 Single results	Olligie results	cm	79	76				
29	Average of the single results	cm	77	7.5		,		
	Smoke temperature							
30	Max. of average	$^{\circ}$	100					
31	Time 1)	min:s	10:00					

Note: 1) time from start of testing

2) Normal Flammability Test according to DIN 4102-1 Clause 6.2

Flame application: [$\sqrt{}$] bottom edge ignition, [] surface ignition
----------------------	-----------	---------------------------	--------------------

Specimen No.	1	2	3	4	5
Reaching the measuring mark within 20 seconds	No	No	No	No	No
Self extinguishing of the flame (s)	15	15	15	15	15
Max. flame height (cm)	4	4	3	4	4
End of afterflaming (s)	15	15	15	15	15
End of afterglowing (s)	15	15	15	15	15
Molten dripping	No	No	No	No	No
Smoke developments (visual impression)	Slight				

All timings are from start of testing

To be continued...

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://www.sgs.com/terms and conditions, him and for electronic Document at <a href="https://www.sgs.com/terms e-document him. Attention is drawn to the limitation of its instruction is usues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its instruction in a subject of the company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their bits and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any finantinized alternators foregor or falsification of the content or appearance of this document is unlawfull and offenders may be prosecuted to the fullest extent of the law. Utilizes otherwise that the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



No. AJD201203114

Date: JUN.27, 2012

Page 5 of 5

Criteria for classification for Class B1 (DIN 4102-1 Clause 6.1.2)

All materials, except flooring, may be classed as B1 materials if they met,

- a) Pass DIN 4102-16 "brandschacht" test if
 - 1) The mean value for the residual length of each specimen is at least 15 cm, and no individual values are lower than 0 cm;
 - 2) The mean effluent temperature does not exceed 200°C in any test;
 - 3) The requirement for the residual length of each specimen is met even where there is afterflame, afterglow, or smouldering.
- Pass DIN 4102-1 Clause 6.2.3 Ignitability Test if,
 For each specimen, flaming doesn't reach the gage mark within 20s after flame application.

STATEMENTS:

This test report does not replace any mandatory certification of the product that may be required.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire and smoke hazard of the product in use.

Photo Appendix:



End of Report